



P P35GB-C40R-4290

Copolymer Polypropylene Reinforced with Glass Fiber

Nirumand Polymer

Product Description

P35GB-C40R-4290 is copolymer polypropylene reinforced with 35% glass fiber. It provides impact resistance, mechanical properties, stiffness, surface hardness, better dimensional stability, good thermal and chemical resistance. This compound is used in appliance industry, automotive applications, electrical goods, housewares and other utility products. This grade is designed to be processed in conventional injection molding techniques.

General Properties

Material Status	•Commercial: Active
Forms	•Pellets
Processing Method	•Injection molding
Color	•Black

Physical Properties	Value	Unit	Test Method
Density	1.2	gr/cm ³	ISO 1183
Melt Mass-flow Rate (MFR) (230°C/2.16 kg)	gr/10 min	ASTM D1238
Shrinkage	< 0.2	%	ASTM D955

Mechanical Properties	Value	Unit	Test Method
Tensile Strength@yield	60	MPa	ISO 527
Tensile Strength@Break	60	MPa	ISO 527
Elongation @ Break	6	%	ISO 527
Elastic Modulus	MPa	ISO 527
Flexural Modulus	5100	MPa	ASTM D790

Impact	Value	Unit	Test Method
Notched Izod Impact (23°C)	9	kJ/m ²	ISO 180
Notched charpy Impact (23°C)	kJ/m ²	ISO 179

Hardness	Value	Unit	Test Method
Durometer Hardness	72	Shore D	ASTM D2240

◆ Values shown are average & are not to be considered as product specifications.

Web-site: www.npolymer.com

E-mail: Sales@npolymer.com

Address: Abbas abad Industrial Zone-Tehran-Iran

Tel: (+9821)35000234 Fax: (+9821)43850755