Technical Data sheet

P30GB H40R

Homopolymer Polypropylene Reinforced with Glass Fiber

Nirumand Polymer



Nirumand Polymer Co.Filled & Reinforced Engineering Plastics

Product Description

P30GB H40R is Recycled Homopolymer Polypropylene reinforced with 30% glass fiber. It provides high mechanical properties, stiffness, surface hardness, better dimensional stability, good heat and chemical resistance. This compound is used in homeappliance industry, automotive applications, electrical goods, housewares and other utility products. This grade is designed to be processed in conventional injection molding techniques.

| General Properties | | | | |
|--|-------------------------------------|---------------------------------|----------------------------------|---|
| Material Status | Commercial: Active | | | |
| Forms | • Pellets | | | |
| Processing Method | Injection molding | | | |
| Color | • Black | | | |
| Physical Properties | | Value | Unit | Test Method |
| Density | | 1.12 | gr/cm ³ | ISO 1183 |
| Melt Mass-flow Rate (MFR) (230°C/2.16 kg) | | •••• | gr/10 min | ASTM D1238 |
| Shrinkage | | < 0.4 | % | Internal |
| Mechanical Properties | | Value | Unit | Test Method |
| Mechanical Propertion | cs | value | Offic | rest Method |
| Tensile Strength@Brea | | 67 | Мра | ISO 527 |
| | | | •• | |
| Tensile Strength@Brea | | 67 | Мра | ISO 527 |
| Tensile Strength@Brea | | 67 4.5 | Mpa % | ISO 527 ISO 527 |
| Tensile Strength@Brea Elongation@Yield Flexural Modulus | ak | 67 4.5 4500 | Mpa % Mpa | ISO 527 ISO 527 ASTM D790 |
| Tensile Strength@Brea Elongation@Yield Flexural Modulus Impact | (23°C) | 67 4.5 4500 Value | Mpa % Mpa Unit | ISO 527 ISO 527 ASTM D790 Test Method |
| Tensile Strength@Brea Elongation@Yield Flexural Modulus Impact Notched Izod Impact (| (23°C) | 67 4.5 4500 Value 6 | Mpa % Mpa Unit kj/m² | ISO 527 ISO 527 ASTM D790 Test Method ISO 180 |

Values shown are average & are not to be considered as product specifications.

Web-site: <u>www.npolymer.com</u> E-mail: <u>Sales@npolymer.com</u>, <u>Trade@npolymer.com</u>

Address: Abbas abad Industrial Zone-Tehran-Iran Tel & Fax: (+9821)35000234