

Technical Data Sheet

V57DB-Bumper UV

Copolymer Polypropylene Toughened with EPDM

Nirumand Polymer



Nirumand Polymer Co.
Filled & Reinforced Engineering Plastics

Product Description

V57DB-Bumper UV is copolymer polypropylene toughened with EPDM and filled with mineral fillers offering high impact strength and UV resistance. This compound is used in automotive applications exposed to UV radiation especially bumper parts and other utility products. This grade is designed to be processed in conventional injection molding process.

Physical Properties	Value	Unit	Test Method
Density	0.9	gr/cm ³	ISO 1183
Melt Mass-flow Rate (MFR) (230°C/2.16 kg)	10	gr/10 min	ASTM D1238
Shrinkage	< 1.7	%	Internal

Mechanical Properties	Value	Unit	Test Method
Tensile Strength @ Yield	≥18	MPa	ISO 527
Tensile Strength @ Break	...	MPa	ISO 527
Elongation @ Break	≥100	%	ISO 527
Flexural Modulus	900	MPa	ASTM D790

Impact	Value	Unit	Test Method
Notched Izod Impact (23°C)	≥ 30	KJ/m ²	ISO 180

Hardness	Value	Unit	Test Method
Durometer Hardness (after 5 S)	57	Shore D	ISO 868

◆ Values shown are average & are not to be considered as product specifications.

Web-site: www.npolymer.com
Address: Abbas abad Industrial Zone-Tehran-Iran

E-mail: Sales@npolymer.com, Trade@npolymer.com
Tel & Fax: (+9821)35000234