Technical Data Sheet

66AN-Supertough

Polyamide 66

Nirumand Polymer



Product Description

66AN-Supertough is polyamide 66 resin offering good balance of mechanical properties and toughness. This compound provides very high impact resistance compared to typical polyamide 66 resin. This product is used in automotive applications, electrical goods, home appliance industry, and other utility products. This grade is designed to be processed in conventional injection molding process.

General Properties				
Material Status	•Commercial: Active			
Forms	• Pellets			
Processing Method	•Injection molding			
Color	• Natural			
Physical Properties		Value	Unit	Test Method
Density		1.11	gr/cm³	ISO 1183
Shrinkage			%	Internal
Mechanical Properties		Value	Unit	Test Method
Tensile Strength @ Yield		≥ 40	MPa	ISO 527
Tensile Strength @ Break		***	%	ISO 527
Elongation @ Break		≥ 45	%	ISO 527
Flexural Modulus		1500	%	ASTM D790
Impact		Value	Unit	Test Method
Notched Izod Impact (23°C)		80	kJ/m²	ISO 180
Notched Izod Impact (-20°C)		65	kJ/m²	ISO 180
Hardness		Value	Unit	Test Method
Vicat Softening Point(50N/ 120°C/hr)		≥ 155	°C	ASTM D1525

Values shown are average & are not to be considered as product specifications.

Web-site: www.npolymer.com E-mail: Sales@npolymer.com, Trade@npolymer.com,

Address: Abbas abad Industrial Zone-Tehran-Iran Tel & Fax: (+9821)35000234